

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
3 August 2006 (03.08.2006)

PCT

(10) International Publication Number
WO 2006/081345 A1

(51) International Patent Classification:

C08G 61/12 (2006.01) **C08G 61/10** (2006.01)
G01N 21/64 (2006.01)

(21) International Application Number:

PCT/US2006/002739

(22) International Filing Date: 25 January 2006 (25.01.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:

60/646,920 25 January 2005 (25.01.2005) US

(71) Applicant (for all designated States except US): **NORTH DAKOTA STATE UNIVERSITY RESEARCH FOUNDATION** [US/US]; 1735 Ndsu Research Park Drive, Fargo, North Dakota 58105-5002 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **BOUDJOUK, Philip** [US/US]; 1735 Ndsu Research Park Drive, Fargo, North Carolina 58105-5002 (US). **THOMAS, Johnson** [US/US]; 1735 Ndsu Research Park Drive, Fargo, North Dakota 58105-5002 (US).

(74) Agent: **MARSH, Wendy**; **MCKEE, VOORHEES & SEASE, PLC**, 801 Grand Avenue, Suite 3200, Des Moines, Iowa 50309 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.


(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

[Continued on next page]

(54) Title: CHROMOPHORE AND POLYMER CAPABLE OF DETECTING THE PRESENCE OF VARIOUS NEUROTOXINS AND METHOD OF USE



(57) Abstract: Applicants have produced a chromophore and a polymer that are highly sensitive to the presence of various agents, including organophosphates, pesticides, neurotoxins, metal ions, some explosives, and biological toxins. The detection is accomplished by detecting a change in the fluorescence characteristics of the chromophore or polymer when in the presence of the agent to be detected. The chromophore and polymer may be incorporated into sensors of various types, and they are adaptable for potential field use in areas where detection of these types of agents is desired.

WO 2006/081345 A1



For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

**TITLE: CHROMOPHORE AND POLYMER CAPABLE OF DETECTING
THE PRESENCE OF VARIOUS NEUROTOXINS AND METHOD
OF USE**

5

CROSS-REFERENCE TO RELATED APPLICATION

This application claims priority to U.S. Provisional Patent Application Serial No. 60/646,920 filed January 25, 2005, which is incorporated by reference herein in its entirety.

10

GRANT REFERENCE

This research was federally funded under Defense Microelectronics Activity (DMA), Department of Defense, Contract No. 1-194003-04-2-0404. The government may have certain rights in this invention.

15

BACKGROUND OF THE INVENTION

A wide variety of toxins exist in nature and they can also be synthetically produced. They vary in their structural complexity, ranging from formic acid produced by ants to protein toxins produced by several bacteria. Neurotoxins are among the most poisonous and fastest acting toxins. They specifically target the nervous system of animals, including humans, by interfering with the transmission of nervous signals. Neurotoxins are generally more lethal than toxins produced by microbes, and can cause incapacitation or death of the affected individual within minutes of exposure. As a result, neurotoxins have been and will continue to be significant potential candidates for weaponization. Examples of weaponized neurotoxins include Tabun (GA), Sarin (GB), Soman (GD), Cyclosarin (GF), DFP, DMMP, and VX, among others.

20
25

Each of these listed neurotoxins, and others, are organophosphates. Their neurotoxic activity arises from their ability to inhibit the functionality of acetylcholine esterase (AChE). Under normal conditions, AChE catalyzes the hydrolysis of the neurotransmitter acetylcholine (ACh) to acetic acid and choline. This reaction allows cholinergic neurons to return to their resting state after activation. In the presence of organophosphates, however, AChE is inhibited and neurons are unable to return to their resting state. In low doses, this results in eye watering and excessive salivation, and in

30

higher doses, individuals are afflicted with various conditions, including salivation, lacrimation, urination, defecation, gastro intestinal upset, and emesis. When dosage is high enough, exposure to these compounds can also result in death. It is these properties of organophosphates that make them particularly suited for use not only as pesticides, but also
5 as potential chemical warfare agents.

Because of this potential use of organophosphates as weapons and the speed with which they attack the human body after exposure, there is a critical need for an efficient method to quickly and accurately detect these highly toxic compounds. While there have been several developments in the past decade for detection of organophosphates, including
10 colorimetric detection methods, surface acoustic wave (SAW) devices, enzymatic assays, and interferometry, each of these has at least one disadvantage. The limitations of these existing methods include slow response time, lack of specificity, low sensitivity, operational complexity or non-portability. For example, two major approaches that have received extensive attention are immuno-based assays and DNA sequencing schemes.
15 However, immuno-based assays are difficult to implement outside of the laboratory because of the instability of the antibodies involved and the necessity of including unstable reagents in the assay. And DNA sequencing techniques are time and instrument-intensive, so therefore they cannot meet the requirements for practical field use. Additionally, both approaches require extensive operator training to be properly implemented.

20 Another common approach to sensing the presence of organophosphates is to rely upon an immobilized AChE detector coupled to a transducer such as Ph electrodes, fiber optics, and piezo electric crystals. This approach, however, is hampered by several limitations. For example, immobilized enzymes are sensitive and detect a broad spectrum of AChE inhibitors. Because of this broad range sensitivity, they lack selectivity and are
25 prone to false positive alerts, particularly when exposed to choline mimics.

In addition to detection of organophosphates, there is a need for any sensor to convert a detector's chemical, mechanical, or optical change into a measurable signal when the organophosphates are present. Many different types of sensors are known in the art. For example, chemical sensors often detect conductivity changes, amperometric changes,
30 or potentiometric changes. Optical sensors detect changes in emission or absorption. Mechanical sensors can detect changes in mechanical properties or impedance. However,

none of the known sensors are or can be linked to a detection sensitive material which provides both quickness of alert and accuracy of detection.

As can be seen from the foregoing, there is a need in the art for development of a way to quickly detect the presence of neurotoxins in such a way that can be utilized in non-laboratory applications, by minimally trained personnel, with a low incidence of false positive alerts.

It is therefore an object of the present invention to provide a neurotoxin-sensitive compound that can selectively detect various organophosphates agents over a range of concentrations and conditions.

A further object of this invention is to provide a compound for use in optoelectronic sensors to detect organophosphates agents.

It is another object of this invention to provide a polymer capable of use in optoelectric sensors for detection of organophosphates agents.

Another object of this invention is to provide a method for detecting organophosphate agents using lumiphoric compounds.

These and other objects of the present invention will become apparent from the description of the invention that follows.

BRIEF SUMMARY OF THE INVENTION

The invention described herein provides a practical method for using organic compounds and/or polymers to detect various bioactive and other types of agents that include halogen or methoxy groups, including organophosphates, neurotoxins, pesticides, metal ions, and combinations thereof. When the detection chromophore or polymer of the invention come in contact with the compound to be detected, the detection compound reacts with a compound to be detected, thereby changing the fluorescence properties of the detection compound. This change in fluorescence can then be measured and indicates the presence of the compound to be detected. The chromophore or polymer may be used in a variety of sensors, including optical electronic sensors, biosensors, and surface acoustic wave sensors for detection of the various organophosphate and other compounds that may be detected.

Transition metal complexes that are luminescent in room-temperature solution have been used in a variety of chemical and biochemical applications. Many of these applications require that the metal lumiphore be functionalized so that it can be appended to a molecule or macromolecule of interest or activated by chemical reaction. Such
5 functionalized lumiphores have been used in electron-transfer studies, in the design of new biosensors, and in the formulation of emissive paints.

In the present invention, the binding capability of pyrazines and aminopyrazines to bind metals and other organic and biomolecules is utilized to synthesize new organic or polymeric materials whose fluorescence properties change when coming into contact with
10 appropriate analytes.

This change in fluorescence characteristics can be used to produce a sensor to assist in the detection of these various compounds. These multi valiant interactions produce a distance-dependent fluorescence energy transfer, and can be used in a reagent-free, highly sensitive, and specific sensing technology for detection of these toxins.
15

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a graph showing the emission spectra of the chromophore of the present invention with dimethylchlorophosphonate (DMCP).

Figure 2 illustrates the UV-Vis absorption and emission spectra of
20 polyparaphenylene derivatives having amino pyrazine units as described in Example 1.

Figure 3 illustrates the intensity of fluorescence of polymer and polymer + dimethylchlorophosphonate (DMCP).

Figure 4 illustrates the intensity of fluorescence of polymer and polymer + dimethyl methylphosphonate (DMMP).
25

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

In its broadest sense, the invention comprises the use of a polymer or chromophore with luminescent properties that are either enabled (in the case of the chromophore) or disabled (in the case of the polymer) in the presence of a compound to be detected, and
30 methods of using said polymer and/or chromophore to detect such compounds. In addition, the invention includes a method of producing the polymer and chromophore.

In a preferred embodiment, a polymer is produced that ceases to fluoresce when contacted with an organophosphate, neurotoxin, pesticide, metal ion, biological agent (or combinations thereof) or other types of compounds containing at least one halogenated group. Specific examples of halogenated neurotoxins include sarin, soman, GF, and DFP.


5 While the present invention specifically refers to the use of detection agents for use in detecting neurotoxins, it is to be understood that the present invention is useful for detection of numerous compounds that contain one or more of the functional groups of interest.

10 In contrast to the polymer, the chromophore of the present invention fluoresces when contacted with an organophosphate, neurotoxin, pesticide, metal ion, biological and/or other types of compounds containing either a halogenated or methoxy-functional group.

The respective modes of detection of the polymer and the chromophore allow an effective dual means of detecting and identifying various compounds containing a
15 halogenated and/or methoxy group. For instance, the chromophore can be used to generally detect the presence of a neurotoxin. Once a neurotoxin is detected, the polymer can be used to more specifically identify whether the neurotoxin is one containing a halogenated group. Alternatively, the polymer and chromophore can also be used individually to detect the presence of various halogenated and/or methoxylated
20 neurotoxins.


The backbone of the polymer is generally made up of some combination of at least one of aminopyrazines, pyrazine, aminopyridine, or any amine containing an aromatic moiety; one or more of thiophene, pyridine, bipyridine, quinoline, isoquinoline, paraphenylene, hydroxyl paraphenylene, a phenyl group, or any hetero aromatic system.
25 The backbone has a total number of between 1 and 100 units, with about 5-20 being preferred. The backbone preferably consists of pyrazine, aminopyridine, or aminopyrazine, with aminopyrazine being most preferred.

Preferred polymers of the present invention have the following general formula:




wherein R_1 is H, alkyl, cycloalkyl, benzyl, or any aromatic, heteroaromatic, or heterocyclic group; and n is an integer between 1 and 100; and R_2 is a $\text{C}_6\text{-C}_{15}$ alkyl chain. Again, n is preferably 5-20.

Most preferred polymers of this invention have the following general formula:




wherein R_1 is H, alkyl, cycloalkyl, benzyl, or any aromatic, heteroaromatic, or heterocyclic group; and n is an integer between 1 and 100, with 5-20 being preferred.

The chromophore of the present invention has the following general formula:




wherein R is H, NH₂, an aliphatic chain, or an aromatic group. The aliphatic chain is preferably C₁-C₈.

Preferred chromophores of the invention have one of the following formulas shown below:



15



The chromophore and polymer are generally prepared by Suzuki coupling reactions. Such reactions are well known and understood in the art. In general, an organoborane is reacted with an organic halide in an organic solvent, such as tetrahydrofuran (THF) and ethers. This reaction preferably occurs in a nitrogen atmosphere with vigorous stirring at a temperature between 90-110°C. However, other temperatures, atmospheres, and reaction conditions are also appropriate, as would be understood to persons skilled in the art. The use of a palladium catalyst is also preferred. Once the reaction is complete, the organic phase is separated and the polymer precipitated therefrom. The precipitated polymer is then separated and dried using conventional means or can be retained in solution.


In the absence of neurotoxins, the polymer fluoresces in the presence of ultraviolet light. However, upon contact with the halogenated phosphate esters of neurotoxins, the polymer quenches the fluorescence of the neurotoxin, thereby facilitating its detection. This fluorescence quenching is the result of the NH_2 group of the conducting polymer hydrolyzing the halogenated phosphate ester and releasing acid which in turn oxidizes the polymer.

The detection of the organophosphate molecule by the change in fluorescence characteristics of the polymer occurs quite rapidly, typically in less than three seconds. Given this fast response time, the polymer is particularly suited for use in optoelectronic sensors.

In addition to the above-described polymer, a non-polymeric chromophore may also be used to detect the presence of the organophosphates and other biological agents already described above. The chromophore has the reverse fluorescence characteristics as the polymer, meaning that in the absence of organophosphate molecules, the chromophore does not fluoresce in the presence of ultraviolet light. The chromophore gains its fluorescence under ultraviolet light when a neurotoxin containing either a methoxy or halogenated group is present. The fluorescence is the result of the reaction of the OH of the chromophore with these functional groups.

The chromophore and polymer have different mechanisms of action to detect the presence of organophosphates or other compounds. Generally, the polymer hydrolyzes the halogenated phosphate ester of the organophosphate molecule and releases acid, which in turn oxidizes the polymer. This leads to formation of imine form of the polymer, which is


not fluorescent after binding with the organophosphate. This imine form is depicted below:



5

Cyclic voltammetry shows that the polymer is oxidized in two steps, and the EIS measurement shows an increase in resistivity with oxidation. It is the increase in resistivity that explains the quenching of the fluorescence in response to the presence of organophosphate or other molecules capable of detection. Figure 3 illustrates the intensity of fluorescence of unbound polymer compared to polymer bound to DMCP. Figure 4 illustrates that polymer bound to dimethylmethylchlorophosphonate (a non-halogenated neurotoxin) has the same intensity of fluorescence as unbound polymer.

As noted, the chromophore detects the presence of organophosphates or other detectable molecules by interaction between the hydroxyl group and the methoxy or halogenated group of the neurotoxin molecule. This leads to a cyclization reaction which in turn produces the fluorescent molecule depicted below. The overall reaction is also shown:



- 5 where A^- is $\text{P O}_2(\text{OCH}_3)_2^-$. Figure 1 is a graph showing the emission spectra of the most preferred chromophore of the present invention (as shown above) with dimethylchlorophosphonate (DMCP).

Based on the above-described mechanisms of action, the chromophore and polymer described are able to detect a wide variety of compounds. The chromophore can detect any
 10 neurotoxin having a methoxy or halogenated group, and the polymer will detect halogenated neurotoxins specifically. Detectable compounds include organophosphates having the requisite halogen or methoxy group, such as sarin, cyclosarin, soman, tabun, diisopropylfluorophosphate, diethylchlorophosphate, VE, VG, VM, VX, metrifionate, pyridostigmine, and physostigmine; explosives such as plastic explosive or trinitrotoluene;
 15 and metal ions, such as iron, cobalt, nickel, copper, a transition metal ion, or a main group metal ion.

For years military force have used detection devices to identify these same materials but even today's best detection measures may require minutes for the user to receive an accurate alert to a potential hazard. Some detectors are quicker but they also provide more
 20 false alerts.

The polymer and chromophore of the present invention can accurately identify trace amounts of poisons or explosives having halogen and/or methoxy functional groups in

seconds. These detection molecules can detect leaks in shipping containers of certain industrial chemicals, detect certain explosive compounds and detect an entire family of neurotoxins. In addition to giving advanced notice to the presence of hazards, the detection molecules can be used to authenticate the elimination of chemical agents or toxic substances during an investigation or clean-up operation.

The polymers of the present invention notify users via multiple feedback methods. They can be set to fluoresce in ultraviolet light yet remain clear in visible light. When in this mode, the fluorescence will quench as a toxic substance or explosive compound comes into contact it. Alternatively, the chromophore can provide no initial ultraviolet fluorescence, but fluoresces upon exposure to a toxic substance or explosive compounds.

The detection molecules of this invention also have the unique property of providing enough electrical activity upon coming into contact with a hazardous substance so that it can be integrated into many of today's existing electrical sensors.

Rapid alert notification to the presence of a fast acting neurotoxin is extremely important. Many chemical agents cause injury or death in less than a minute. Speed is also essential when multiple yet rapid and economical detections must be made (for example, hand screening of luggage). The detection molecules of the present invention provide accurate detection within 2 to 3 seconds of contact with a target substance as compared to minutes with similar technologies. These unique molecules are designed to detect trace amounts of:

- the entire family of halogenated chemical compounds with very high selectivity;
- the chemical warfare agents VX, GF, GB (Sarin), GD, (Soman) and GA (Tabun);
- explosives (various plastic explosives and TNT); and
- pesticides (organo-phosphonates like DFP and DMMP).

The detection molecules need only be applied in strengths ranging from parts-per-millions to part-per-billions. Further, under certain circumstances, the molecules can be reconditioned for repetitive use.

The detection molecules of the instant invention can be applied separately or together, and as an individual coating or mixed with other coatings. They can be sprayed

or painted on to a surface, and can be applied to such simple materials a tape or cloth swabs, or applied to much more complex devices such as electronic sensors or electronic noses. Sensors incorporating either or both of the chromophore and/or polymer can be easily used in any location in which fast detection of neurotoxins is desired. Examples
5 might include potential targets for terrorist attacks, such as subways, airports, aircraft, or government buildings. The basic performance and functionality of these molecules in detecting neurotoxins have been verified with fluorescence measurements, impedance testing and cyclic voltammetry.

In addition to being used to detect neurotoxins in the context of terrorism or
10 chemical warfare, the polymer and chromophore described can also be used to detect the presence of organophosphates in the context of medical diagnosis or treatment monitoring. In fact, the polymer and chromophore may be used to detect neurotoxins in virtually any desired application.

The following examples are offered to illustrate but not limit the invention. Thus,
15 they are presented with the understanding that various formulation modifications as well as method of delivery modifications may be made and still be within the spirit of the invention.

EXAMPLE 1

20 Preparation and Properties of a Preferred Polymer

A preferred polymer of the present invention was prepared by the following method:

a) 2, 5-Dibromo-4-dodecyloxy phenol

25 2,5-Dibromohydroquinone 3 (40.2 g, 0.15 mol) was dissolved in a solution of sodium hydroxide (9.2 g, 0.23 mol) in 1.5 L of absolute ethanol at room temperature under nitrogen atmosphere. The reaction mixture was warmed to 50 - 60°C with constant stirring. The dodecylbromide (36 ml, 0.15 mol) was added drop wise to the above reaction mixture at 60 °C. After 10 h of stirring under nitrogen atmosphere, the reaction mixture
30 was cooled and the precipitate formed was filtered and washed with methanol. This precipitate was identified as diallelated-2,5-dibromohydroquinone as a side product. The

filtrate was evaporated to remove the solvent. 2 L of distilled water was added to the residue and the mixture was acidified with 36% HCl, boiled gently for 1 h and cooled. The resulting precipitate was collected by filtration, washed with water and dried in *vacuo*. The crude product was purified by column chromatography using a mixture of solvents

5 (CH₂Cl₂ : hexanes, 4 : 6) to get the pure product in 60% yield.

¹H NMR, (CDCl₃, δ ppm): 7.25 (s, 1H), 6.97 (s, 1H), 5.16 (s, 1H), 3.92 (t, 2H), 1.62 (q, 2H), 1.4 (m, 18H); 0.88 (t, 3H). ¹H NMR (CDCl₃, δ ppm): 7.25 (s, 1H), 6.97 (s, 1H), 3.92 (t, 2H), 1.80 (q, 2H), 1.4 (m, 18H); 0.87 (t, 3H). ¹³C NMR (CDCl₃, δ ppm): 149.95, 146.64, 120.16, 116.49, 112.34, 108.26, 70.25, 31.81, 29.55, 29.47, 29.26, 29.20, 28.97, 10
25.82, 22.60, 14.04.

b) 2,5-Dibromo-1-benzyloxy-4-dodecyloxy benzene

Benzyl bromide (3.8 ml, 0.031 mol) was added drop wise to a stirred solution of 2,5-dibromo-4-dodecyloxy phenol (a) (6.95 g, 0.015 mol) and anhydrous K₂CO₃ (3.28 g, 0.023 mol) in 700 ml of absolute ethanol at 40- 50 °C. The reaction mixture was stirred for
15 10 h at 50°C, progress of the reaction was monitored using TLC, cooled to RT and evaporated to remove the solvent. An equal volume of distilled water was added to the residue and the mixture was stirred for one hour at 0°C. The resulting precipitate was collected by filtration, washed with water, and dried in vacuum. Recrystallization was done in methanol to get 80% yield.

20 ¹H NMR (CDCl₃, δ ppm): 7.46 (m, 5H), 7.21 (s, 1H), 7.15 (s, 1H), 5.11 (s, 2H), 3.99 (t, 2H), 1.85 (q, 2H), 1.32 (m, 18H), 0.95 (t, 3H). ¹³C NMR (CDCl₃, δ ppm): 150.51, 149.49, 136.16, 128.50, 128.10, 127.17, 119.32, 118.31, 111.53, 111.01, 71.99, 70.19, 31.83, 29.56, 25.84, 22.60, 14.02

c) 1-Benzyloxy-4-dodecyloxyphenyl-2,5-bisboronic acid

25 1.6 M Solution of butyl lithium in hexanes (55 ml, 0.088 mol) was added slowly to a solution of dibromide b (11.57 g, 0.022 mol) in a mixture of solvents diethyl ether (150 ml) and THF (150 ml) under nitrogen atmosphere at -78°C. The solution was warmed to RT and cooled again to -78°C. Triisopropyl borate (51 ml) was added drop wise within 2 h. After complete addition, the mixture was warmed to RT and stirred overnight. Water
30 was added and the mixture stirred for 24 h. The crystalline mass was recovered by filtration. The product was re crystallized from acetone in 80% yield.

¹H NMR (DMSO-d₆, δ ppm): 7.80 (s, 2H), 7.75 (s, 2H), 7.46 (m, 5H), 7.29 (s, 1H), 7.17 (s, 1H), 5.11 (s, 2H), 3.99 (t, 2H), 1.73 (q, 2H), 1.24 (m, 18H), 0.85 (t, J= 6 Hz, 3H). ¹³C NMR (DMSO-d₆, δ PPM): 157.00, 156.22, 137.16, 128.38, 127.77, 127.52, 118.28, 117.70, 70.05, 68.30, 31.2, 28.89, 25.38, 22.00, 13.87.

5 **d) 1-Benzyl-4-dodecyloxy phenyl-2,5-bis(trimethylene boronate)**

Diboronic acid c (8.2 g, 0.018 mol) and trimethylene glycol (5.2 in], 0.072 mol) were added to toluene (150 ml) at RT. Then the reaction mixture was refluxed for 3h. The solvent was removed by rotovap. The residue was dissolved in CHCl₃, dried over sodium sulfate and filtered. The solution was evaporated and the residue was re crystallized from
10 hexanes. The recrystallized product was used without further purification for polymerization.

¹H NMR (CDCl₃, δ ppm): 7.35 (m, 5H), 5.05 (s, 2H), 4.16 (d, 8H), 3.85 (t, 3H), 2.02 (m, 4H), 1.57 (m, 2H), 1.27 (m, 18H), 0.88 (t, 3H). ¹³C NMR (CDCl₃, δ ppm): 157.73, 156.92, 138.28, 128.06, 127.00, 120.42, 119.79, 71.70, 69.70, 61.91, 31.81, 29.55, 27.22,
15 25.98, 22.57, 14.01.

e) 2-Amino-3, 5-dibromopyrazine

Under absence of light and at 0°C, N-bromosuccinimide (15.68 g, 88.1 mmol) was added to a solution of 2-aminopyrazine (4.19 g, 44.06 mmol) in dry dichloromethane (250 ml). The mixture was stirred for 20 h at 4°C and then washed with four 40 ml portions of a
20 saturated sodium carbonate solution in water. The organic layer was dried (MgSO₄) and evaporated under reduced pressure, affording the title compound as 12.8 g of a light brown solid. Column chromatography, using silica and a dichloromethane/ethyl acetate (3/1) mixture as the eluent, yielded pure 2-amino-3,5-dibromopyrazine as 5.00 g (65%) of a light yellow solid.


25 ¹H-NMR (CDCl₃, 400 Mhz): 8.09 (s, 1H), 4.95 (2H, NH) ppm. ¹³C-NMR (CDCl₃): 153.5 (C-2), 144.3, 131.9, 126.8 ppm

f) Synthesis of Poly(p-phenylene)-co-amino pyrazine polymer

Diboronic ester d (0.97 g, 1.86 mmol) and dibromo aminopyrazine e (0.458, 0.186 mmol) were added to dry THF (10 ml) under nitrogen atmosphere. 2M Na₂CO₃ (15 ml)
30 was added to this followed by palladium catalyst tetrakis(triphenylphosphino)palladium (1.5 mol % with respect to monomer d). The mixture was then heated to 100°C for 72 h in

a flask with vigorous stirring. After the reaction, the organic phase was separated and the polymer precipitated from hexane. The precipitated polymer was separated and dried to yield 0.5 g of polymer (Yield=60%). GPC analysis showed a number average molecular weight of 5300.

5 This leads to production of the following preferred polymer:



10

EXAMPLE 2

Preparation of a Preferred Chromophore

a) Benzyl bromide (7 ml, .05mol) was added drop wise to a stirred solution 2
bromo phenethyl alcohol (10 g, 0.0496 mol) and anhydrous NaH (2.28 g, 0.05 mol) in 100
15 ml of dry THF at 40- 50°C. The reaction mixture was stirred for 10 h at 50°C, progress of
the reaction was monitored using TLC, cooled to RT and evaporated to remove the solvent.
An equal volume of distilled water was added to the residue and the mixture was stirred for
one hour at ambient. The organic layer was separated, dried and evaporated. To the
resulting liquid 100ml of 5% ethanolic solution of NaOH was added and refluxed for 3 hr.
20 The resulting solution was evaporated and extracted with ether to give the benzyl protected
phenethyl alcohol as a clear liquid at 80% yield.

¹H-NMR (CDCl₃, 400 Mhz): 7.5 (d, 1H), 7.3 (m, 7H), 7.08 (d, 1H), 4.53 (s, 2H), 3.7 (t, 2H), 3.07 (t, 2H) ppm. ¹³C-NMR (CDCl₃, 100 Mhz): 138.43, 132.96, 131.37, 129.01, 128.58, 128.20, 127.78, 127.76, 127.57, 124.87, 73.12, 69.56, 36.71 ppm.

b) 1.6 M Solution of butyl lithium in hexanes (66 ml, 0.1 mol) was added slowly to a solution of 2-bromo O-benzyl phenethyl alcohol (9.7 g, 0.033 mol) in a mixture of solvents diethyl ether (150 ml) and THF (150 ml) under nitrogen atmosphere at -78°C. The solution was warmed to RT and recooled to -78°C. Triisopropylborate (23.1 ml) was added drop wise within 2 h. After complete addition, the mixture was warmed to RT and stirred overnight. Water was added and the mixture stirred for 24 h. The organic phase was separated and column chromatography of the resulting viscous liquid using dichloromethane as the eluent gave the boronic acid as white crystalline solid in 65% yield. ¹H-NMR (CDCl₃, 400 Mhz): 7.8 (d, 1H), 7.4 (t, 2H), 7.3 (m, 4H), 7.2 (d, 1H), 7.1 (d, 1H), 4.53 (s, 2H), 3.75 (t, 2H), 3.07 (t, 2H) ppm. ¹³C-NMR (CDCl₃, 100 Mhz): 143.78, 136.79, 134.15, 130.44, 129.32, 128.69, 128.20, 127.95, 126.13, 73.74, 72.47, 36.89 ppm.


c) Under absence of light and at 0°C, N-bromosuccinimide (7.84 g, 44.05 mmol) was added to a solution of 2-aminopyrazine (4.19 g, 44.06 mmol) in dry dichloromethane (250 ml). The mixture was stirred for 20 h at 4°C and then washed with four 40 ml portions of a saturated sodium carbonate solution in water. The organic layer was dried (MgSO₄) and evaporated under reduced pressure, affording the title compound as 5.90 g of a light brown solid. Column chromatography, using silica and a dichloromethane/ethyl acetate (3/1) mixture as the eluent, yielded pure 2-bromo-5-aminopyrazine as 5.00 g (65%) of a light yellow solid. ¹H-NMR (CDCl₃, 400 Mhz): 8.09 (s, 1H, H-6), 7.77 (s, 1H, H-3), 4.65 (bs, 2H, NH) ppm. ¹³C-NMR (CDCl₃, 100 Mhz): 153.5 (C-2), 144.3 (C-6), 131.9 (C-3), 126.8 (C-5) ppm.

d) The boronic acid (0.8 g, 3.26 mmol) and bromo pyrazine (0.56 g, 3.26 mmol) were added to dry toluene (20 ml) under nitrogen atmosphere. 2M Na₂CO₃ (15 ml) was added to this followed by palladium catalyst tetrakis (triphenylphosphino) palladium (1.5 mol % with respect to boronic acid). The mixture was then heated to 80 °C for 48 h with vigorous stirring. The reaction mixture was evaporated, washed with water and the organic phase was separated. Column chromatography of the compound using 1:1 Ethyl Acetate/ Hexane mixture gave 60% of the required product.

¹H-NMR (CDCl₃, 400 Mhz): 8.15 (s, 1H), 8.01 (s, 1H), 7.25 (m, 9H), 4.58 (s, 2H, -NH), 4.6 (s, 2H), 3.6 (t, 2H), 3.01 (t, 2H)ppm. ¹³C-NMR (CDCl₃, 100 Mhz): 152.95, 145.20, 141.98, 138.65, 137.71, 137.33, 131.28, 130.85, 130.10, 128.56, 127.80, 127.71, 126.73, 72.97, 71.20, 33.64.

- 5 e) The O-benzyl protected compound was dissolved in a mixture of dry THF (50 ml) and absolute ethanol (50 ml) at RT. 10 % Pd/C (3 g) was added to the above solution. The mixture was flushed with nitrogen gas three times. Two to three drops of *conc.* HCl was added to enhance the debenzylation. The reaction was carried out at RT under positive pressure of hydrogen for 24 h with constant stirring. The reaction mixture
- 10 was filtered through celite powder and the precipitate was washed with absolute ethanol. The filtrate was evaporated and dried in vacuum to yield the desired Chromophore at 50% yield.
- ¹H-NMR (CDCl₃, 400 Mhz): 8.19 (s, 1H), 8.06 (s, 1H), 7.30 (m, 4H), 4.78 (s, 2H, -NH), 3.6 (t, 2H), 3.05 (t, 2H)ppm. ¹³C-NMR (CDCl₃, 100 Mhz): 153.08, 145.20, 141.98, 138.65,
- 15 137.71, 131.28, 130.85, 128.56, 126.73, 64.26, 33.64.

This yields the preferred chromophore below:



- Having described the invention with reference to particular compositions, theories
- 20 of effectiveness, and the like, it will be apparent to those of skill in the art that it is not intended that the invention be limited by such illustrative embodiments or mechanisms, and that modifications can be made without departing from the scope or spirit of the invention, as defined by the appended claims. It is intended that all such obvious

modifications and variations be included within the scope of the present invention as defined in the appended claims. The claims are meant to cover the claimed components and steps in any sequence which is effective to meet the objectives there intended, unless the context specifically indicates to the contrary.

What is claimed is:

1. A polymer comprising: a structure selected from the group consisting of

(a) $\text{---}(\text{---PZ---PPP---})_n\text{---}$,

(b) $\text{---}(\text{---PZ---Ar---})_n\text{---}$, and

5 (c) $\text{---}(\text{---PZ---PPP---Ph---})_n\text{---}$,

wherein PZ is amino pyrazine, pyrazine, amino pyridine, or any amine-containing aromatic moiety; PPP is poly paraphenylene; Ar is thiophene, pyridine, bipyridine, or any heteroaromatic system; Ph is phenyl or an Ar group; and n is an integer between 1 and 100.


10

2. The polymer of claim 1 wherein said heteromatic system is selected from the group consisting of pyrazine, amino pyrazine, thiophene, pyridine, quinoline, isoquinoline, paraphenylene, and hydroxy paraphenylene.

15

3. The polymer of claim 2 wherein PZ is amino pyrazine.

4. The polymer of claim 1 having the following structure:




20

wherein R_1 is H, alkyl, cycloalkyl, benzyl, or any aromatic, heteroaromatic, or heterocyclic group; R_2 is a C_6 - C_{15} alkyl; and n is an integer between 1 and 100.

5. The polymer of claim 4 wherein n is an integer between 5-20.

6. The polymer of claim 4 having the following structure:

5



wherein R_1 is H, alkyl, cycloalkyl, benzyl, or any aromatic, heteroaromatic, or heterocyclic group; and n is an integer between 1 and 100.

10

7. The polymer of claim 6 wherein R_1 is H.


8. The polymer of claim 1 that fluoresces when exposed to ultraviolet light.

15 9. The polymer of claim 8 that ceases to fluoresce when contacted with a compound containing a halogenated group.

10. The polymer of claim 8 wherein the contact causes the fluorescence to cease in less than 5 seconds.


20

11. A chromophore having the following structure:




wherein R is H, NH₂, an aliphatic chain, or an amino group.

12. The chromophore of claim 11 wherein the aliphatic chain is C₁-C₈.
13. The chromophore of claim 11 having one of the following general formulas:



5



14. The chromophore of claim 11 that fluoresces in the presence of ultraviolet light when contacted with a compound containing a substituent selected from the group consisting of methoxy, halogen, and combinations thereof.
- 5 15. The chromophore of claim 11 wherein the contact causes the fluorescence to appear in less than 5 seconds.
16. A method of detecting a harmful compound comprising: contacting the polymer of claim 1 with a substance suspected of containing a halogen-substituted compound; 10 allowing the polymer to contact the substance for a time period sufficient for the polymer to bind a halogen-substituted compound that may be present; and monitoring the polymer to determine whether there is a change in the fluorescence characteristics of the polymer.
- 15 17. The method of claim 16 wherein the substance is an organophosphate selected from the group consisting of sarin, cyclosarin, soman, tabun, diisopropylfluorophosphate, diethylchlorophosphate, VE, VG, VM, VX, metrifionate, pyridostigmine, and physostigmine.
- 20 18. The method of claim 16 wherein the substance is a plastic explosive or trinitrotoluene.
19. The method of claim 16 wherein the substance is a metal ion selected from the group consisting of iron, cobalt, nickel, copper, a transition metal ion, and a main 25 group metal ion.
20. The method of claim 16 wherein the polymer is monitored to detect a loss of the polymer's fluorescence in the presence of ultraviolet light.
- 30 21. The method of claim 16 wherein the polymer is monitored by noting a change in the electrical activity of the polymer.

22. The method of claim 16 wherein a halogen-substituted compound that is present is detected in a time period of less than five seconds.

5 23. A method of detecting a harmful compound comprising: contacting the chromophore of claim 11 with a substance suspected of containing a compound having a substituent selected from the group consisting of halogen, methoxy, and combinations thereof; allowing the chromophore to contact the substance for a time period sufficient for the polymer to bind a compound that may be present; and
10 monitoring the chromophore to determine whether there is a change in the fluorescence characteristics of the chromophore.

24. The method of claim 23 wherein the compound is an organophosphate selected from the group consisting of sarin, cyclosarin, soman, tabun,
15 diisopropylfluorophosphate, diethylchlorophosphate, VE, VG, VM, VX, metrifionate, pyridostigmine, and physostigmine.

25. The method of claim 23 wherein the compound is a plastic explosive or trinitrotoluene.
20

26. The method of claim 23 wherein the compound is a metal ion selected from the group consisting of iron, cobalt, nickel, copper, a transition metal ion, and a main group metal ion.

25 27. The method of claim 23 wherein the chromophore is monitored by noting the presence of fluorescence of the chromophore under ultraviolet light.

28. The method of claim 23 wherein the compound is monitored by noting a change in the electrical activity of the chromophore.
30

29. The method of claim 23 wherein a compound having a substituent selected from the group consisting of methoxy, halogen, or both is detected in a time period of less than five seconds.

5 30. A method of detecting a harmful compound comprising: contacting a composition comprising the polymer of claim 1 and the chromophore of claim 11 with a substance suspected of containing a compound having a substituent selected from the group consisting of halogen, methoxy, and combinations thereof; allowing the composition to contact the substance for a time period sufficient for at least one of
10 the polymer or the chromophore to bind a compound that may be present; and monitoring the composition to determine whether there is a change in the fluorescence characteristics of the chromophore.

15 31. A composition for detecting a harmful compound comprising: the polymer of claim 1; and the chromophore of claim 11.

32. A sensor for detecting a harmful compound comprising the polymer of claim 1; said harmful compound having a halogen substituent.

20 33. The sensor of claim 32 selected from the group consisting of optoelectronic sensor, biosensor, and surface acoustic wave sensor.

34. A sensor for detecting a harmful compound comprising the chromophore of claim 11; said harmful compound having a substituent selected from the group consisting
25 of halogen, methoxy, and combinations thereof.

35. The sensor of claim 34 selected from the group consisting of optoelectronic sensor, biosensor, and surface acoustic wave sensor.

1/4




Fig. 1

2/4




Fig. 2




Fig. 3

4/4




Fig. 4

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2006/002739

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08G61/12 G01N21/64 C08G61/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08G G01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99/57222 A (MASSACHUSETTS INSTITUTE OF TECHNOLOGY) 11 November 1999 (1999-11-11) claims 1,48,50; examples	1,16-22
X	MARCIA W.C. DEZOTTI, MARCO-A. DE PAOLI: "Poly(p-phenylene-co-2,5-pyrazine), A New Electrically Conductive Polymer" SYNTHETIC METALS, vol. 29, 1989, pages E41-E45, XP002385620 the whole document	1-3,8-10

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

16 June 2006

Date of mailing of the international search report

03/07/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

West, N

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2006/002739

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9957222	A	11-11-1999	AT 261483 T	15-03-2004
			DE 69915466 D1	15-04-2004
			DE 69915466 T2	20-01-2005
			EP 1080162 A1	07-03-2001
